



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : C08G 18/00, C08H 5/00, C08J 9/34, C08L 75/00		A1	(11) International Publication Number: WO 00/15684 (43) International Publication Date: 23 March 2000 (23.03.00)
(21) International Application Number: PCT/US99/21511 (22) International Filing Date: 17 September 1999 (17.09.99) (30) Priority Data: 09/154,340                      17 September 1998 (17.09.98)    US (63) Related by Continuation (CON) or Continuation-in-Part (CIP) to Earlier Application US                                      09/154,340 (CIP) Filed on                              17 September 1998 (17.09.98) (71) Applicant (for all designated States except US): URETHANE SOY SYSTEMS COMPANY, INC. [US/US]; 301 W. South Street, Dover, IL 61323 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): KURTH, Thomas, M. [US/US]; 16910 - 2200 North, Princeton, IL 61356 (US). (74) Agent: VAN THOMME, Todd, A.; Price, Heneveld, Cooper, DeWitt & Litton, 695 Kenmoor, S.E., P.O. Box 2567, Grand Rapids, MI 49501 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  Published With international search report. With amended claims.	
(54) Title: IMPROVED CELLULAR PLASTIC MATERIAL			
(57) Abstract			
<p>An improved cellular material comprises a urethane foam that is the reaction product of soy oil, an isocyanate, and a cross-linker. The soy oil replaces the polyol typically generally required in the production of urethanes. Because the replaced polyol is a petrochemical, use of a renewable and environmentally friendly material such as soy oil is most advantageous. Further, plastic materials of many final qualities may be formed using a single vegetable oil. In addition to cellular foams, solid plastic elastomers may be formed.</p>			

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

IMPROVED CELLULAR PLASTIC MATERIALBACKGROUND OF THE INVENTION

Because of their widely ranging mechanical properties and their ability to be relatively easily machined and formed, plastic foams and elastomers have found wide use in a multitude of industrial and consumer applications. In particular, urethane foams and elastomers have been found to be well suited for many applications. Automobiles, for instance, contain a number of components, such as cabin interior parts, that are comprised of urethane foams and elastomers. Such urethane foams are typically categorized as flexible, semi-rigid, or rigid foams with flexible foams generally being softer, less dense, more pliable, and more subject to structural rebound subsequent to loading than rigid foams.

The production of urethane foams and elastomers are well known in the art. Urethanes are formed when isocyanate (NCO) groups react with hydroxyl (OH) groups. The most common method of urethane production is via the reaction of a polyol and an isocyanate which forms the backbone urethane group. A cross-linking agent may also be added. Depending on the desired qualities of the final urethane product, the precise formulation may be varied. Variables in the formulation include the type and amounts of each of the reactants.

In the case of a urethane foam, a blowing agent is added to cause gas or vapor to be evolved during the reaction. The blowing agent creates the void cells in the final foam, and commonly is a solvent with a relatively low boiling point or water. A low boiling solvent evaporates as heat is produced during the exothermic isocyanate/polyol reaction to form vapor bubbles. If water is used as a blowing agent, a reaction occurs between the water and the isocyanate group to form an amine and carbon dioxide (CO<sub>2</sub>) gas in the form of bubbles. In either case, as the reaction proceeds and the material solidifies, the vapor or gas bubbles are locked into place to form void cells. Final urethane foam density and rigidity may be controlled by varying the amount or type of blowing agent used.

A cross-linking agent is often used to promote chemical cross-linking to result in a structured final urethane product. The particular type and amount of cross-linking agent used will determine final urethane properties such as elongation, tensile strength, tightness of cell structure, tear resistance, and hardness. Generally, the degree of cross-linking that occurs correlates to the flexibility of the final foam product. Relatively low molecular

weight compounds with greater than single functionality are found to be useful as cross-linking agents.

Catalysts may also be added to control reaction times and to effect final product qualities. The effects of catalysts generally include the speed of the reaction. In this respect, the catalyst interplays with the blowing agent to effect the final product density. The reaction should proceed at a rate such that maximum gas or vapor evolution coincides with the hardening of the reaction mass. Also, the effect of a catalyst may include a faster curing time so that a urethane foam may be produced in a matter of minutes instead of hours.

Polyols used in the production of urethanes are petrochemicals. Polyester polyols and polyether polyols being the most common polyols used in urethanes production. For rigid foams, polyester or polyether polyols with molecular weights greater than 6,000, are generally used. For semi-rigid foams, polyester or polyether polyols with molecular weights of 3,000 to 6,000 are generally used, while for flexible foams, shorter chain polyols with molecular weight of 600 to 4,000 are generally used. There is a very wide variety of polyester and polyether polyols available for use, with particular polyols being used to engineer and produce a particular urethane elastomer or foam having desired particular final toughness, durability, density, flexibility, compression set ratios and modulus, and hardness qualities. Generally, lower molecular weight polyols and lower functionality polyols tend to produce more flexible foams than do heavier polyols and higher functionality polyols. In order to eliminate the need to produce, store, and use different polyols, it would be advantageous to have a single versatile component that was capable of being used to create final urethane foams of widely varying qualities.

Further, use of petrochemicals such as polyester or polyether polyols is disadvantageous for a variety of reasons. As petrochemicals are ultimately derived from petroleum, they are a non-renewable resource. The production of a polyol requires a great deal of energy, as oil must be drilled, extracted from the ground, transported to refineries, refined, and otherwise processed to yield the polyol. These required efforts add to the cost of polyols and to the disadvantageous environmental effects of its production. Also, the price of polyols tends to be somewhat unpredictable as it tends to fluctuate based on the fluctuating price of petroleum.

Also, as the consuming public becomes more aware of environmental issues, there are distinct marketing disadvantages to petrochemical based products. Consumer demand for "greener" products continues to grow. As a result, it would be most advantageous to replace polyester or polyether polyols, as used in the production of urethane elastomers and foams, with a more versatile, renewable, less costly, and more environmentally friendly component.

Efforts have been made to accomplish this. Plastics and foams made using fatty acid triglycerides derived from vegetables have been developed, including soybeans derivatives. Because soybeans are a renewable, relatively inexpensive, versatile, and environmentally friendly, they are desirable as ingredients for plastics manufacture. Soybeans may be processed to yield fatty acid triglyceride rich soy oil and protein rich soy flour.

Unlike urethanes, many plastics are protein based. For these types of plastics, soy protein based formulations have been developed. U.S. Patent No. 5,710,190, for instance, discloses the use of soy protein in the preparation of a thermoplastic foam. Such plastics, however, are not suitable for use in applications that call for the particular properties of urethanes. Since urethanes don't utilize proteins in their formulations, soy proteins are not relevant to the manufacture of urethanes.

Epoxidized soy oils, in combination with polyols, have also been used to formulate plastics and plastic foams, including urethanes. For example, U.S. Patent No. 5,482,980 teaches using an epoxidized soy oil in combination with a polyol to produce a urethane foam. A polyester or polyether polyol remains in the formulation, however. Also, as the epoxidation processing of the soy oil requires energy, material and time, use of an unmodified soy oil would be more advantageous.

Efforts have been made to produce a urethane type cellular plastic from un-modified soy oil. U.S. Patents Nos. 2,787,601 and 2,833,730 disclose a rigid cellular plastic material that may be prepared using any of several vegetable oils, including soy oil as a prepolymer component only. The foam disclosed in these patents is made from a multistep process requiring the initial preparation of a prepolymer. Moreover, in the case of U.S. Patent No. 2,833,730, relatively low cross-linker concentrations are urged, resulting in questionable product stability. Further, use of a particular isocyanate, namely toluene diisocyanate, is disclosed, which is disadvantageous due to its relatively high toxicity.

An unresolved need therefore exists in industry for a urethane elastomer, a urethane foam, and a method of producing such materials that are based on a reaction between isocyanates alone or as a prepolymer, in combination with, a vegetable oil or a vegetable oil-polyurea polyol blend, are particularly desirable because they are relatively inexpensive, versatile, renewable, environmentally friendly material such as vegetable oils as a replacement for polyether or polyester polyols typically employed.

### SUMMARY OF THE INVENTION

The present invention is a cellular material that is the reaction product of an A-side and a B-side, where the A-side is comprised of a diisocyanate and the B-side comprises a vegetable oil, a cross-linking agent comprised of a multi-functional alcohol, and a catalyst. The present invention further comprises a method for preparing a cellular material comprising the reactive product of an A-side comprised of a prepolymer diisocyanate and a B-side. The B-side comprises a first vegetable oil, a cross-linking agent comprised of a multi-functional alcohol, a catalyst, and a blowing agent.

Yet another aspect of the invention is a method of preparing a cellular material comprising the steps of combining an A-side material with a B-side material. The A-side comprises a diisocyanate and the B-side material comprises a vegetable oil, a cross-linking agent comprised of a multi-functional alcohol, a catalyst, and a blowing agent.

These and other features, advantages and objects of the present invention will be further understood and appreciated by those skilled in the art by reference to the following specification and claims.

### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The preparation of urethanes is well known in the art. They are generally produced by the reaction of petro-chemical polyols, either polyester or polyether, with isocyanates. The flexibility or rigidity of the foam is dependent on the molecular weight and functionality of the polyol and isocyanate used.

Petrochemical polyol-based polyurethanes can be prepared in a one step or a two step process. In the one step process, what is known in the art as an A-side reactant is combined with what is known as a B-side reactant. The A-side is generally considered to comprise an isocyanate or a mixture of diisocyanate. The diisocyanates typically used are

diphenylmethane diisocyanate (MDI) or toluenediisocyanate (TDI). The particular isocyanate chosen will depend on the particular final qualities desired in the urethane.

5 The B-side material is generally a solution of a petroleum-based polyester or polyether polyol, cross-linking agent, and blowing agent. A catalyst is also generally added to the B-side to control reaction speed and effect final product qualities. As discussed *infra*, the use of a petrochemical such as a polyester or polyether polyol is undesirable for a number of reasons.

10 It has been discovered, however, that flexible urethane foams of a high quality can be prepared by substituting the petroleum-based polyol in the B-side preparation with a vegetable oil in the presence of a multi-functional alcohol cross-linking agent. The molar ratio of the hydroxyl (OH) groups of the cross-linking agent hydroxyl (OH) groups to the vegetable oil is preferably at least 0.7:1, and most preferably between about 0.7 and 1.2 :1. The replacement is made on a substantially 1:1 weight ratio of vegetable oil for replaced petroleum-based polyol. Alternatively, a blend of petroleum-based polyol and vegetable oil  
15 may be used. The process of producing the urethane does not change significantly with the petroleum-based polyol replaced by the vegetable oil with all other components and general methods as are generally known in the art. The qualities of the final flexible, semi-rigid, or rigid urethane foam produced using the vegetable oil are consistent with those produced using a high grade, expensive polyol.

20 Further, using a single vegetable oil, urethane foams of varying and selectable final qualities, including differing flexibility, density, and hardness, can be made by varying only the primary reactants. It would be difficult, if not impossible, to create such varied final foams using a single petroleum-based polyester or polyether polyol with the same variations in the remaining reactants. Instead, different petroleum-based polyols would be  
25 required to produce such varied results.

30 The use of vegetable oil in the urethane forming reaction also realizes a significant cost savings. Vegetable oils are abundant, renewable, and easily processed commodities, as opposed to polyols, which petroleum derivatives and which entail significant associated processing costs. As such, they may currently be acquired for a cost of approximately half that of average grade petroleum-based polyurea, polyester or polyether polyols, and approximately one quarter the cost of high grade petroleum-based polyester or polyether polyols. Also, as polyols derived from petroleum, they are not renewable and carry a

certain environmental cost with them. There is a distinct marketing advantage to marketing products that are based on environmentally friendly, renewable resources such as vegetable oils.

5 The A-side isocyanate reactant of the urethane of the invention is preferably comprised of an isocyanate chosen from a number of suitable isocyanates as are generally known in the art. Different isocyanates may be selected to create different properties in the final product. The A-side reactant of the urethane of the invention comprises diisocyanate; 4,4' diphenylmethane diisocyanate; 2,4 diphenylmethane diisocyanate; and modified diphenylmethane diisocyanate. Preferably, a modified diphenylmethane diisocyanate is used. It should be understood that mixtures of different isocyanates may also be used.

10 The A-side of the reaction may also be a prepolymer isocyanate. The prepolymer isocyanate is the reaction product of an isocyanate, preferably a diisocyanate, and most preferably some form of diphenylmethane diisocyanate and a vegetable oil. The vegetable oil can be soy oil, rapeseed oil, cottonseed oil, or palm oil, or any other oil having a suitable number of reactive hydroxyl (OH) groups. The most preferred vegetable oil is soy oil. To create the prepolymer diisocyanate, the vegetable oil and isocyanate are mixed in a 1:1 ratio for 10-15 seconds every 10-15 minutes for a total of 4 hours or until the reaction has ended. There will still be unreacted isocyanate (NCO) groups in the prepolymer. However, the total amount of active A-side material has increased through this process.

15 The prepolymer reaction reduces the cost of the A-side component by decreasing the amount of isocyanate required and utilizes a greater amount of inexpensive, environmentally friendly soy oil. In order to permit the prepolymer diisocyanate A-side to react with the B-side, additional isocyanate must be added to elevate the isocyanate (NCO) level to an acceptable level.

20 The B-side reactant of the urethane reaction includes at least vegetable oil and a cross-linking agent. Typically, a blowing agent and a catalyst are also included in the B-side. It is believed that the isocyanate reacts with the fatty acids of the vegetable oil to produce the polymeric backbone of the urethane.

25 The vegetable oils that are suitable for use tend to be those that are relatively high in triglyceride concentration and that are available at a relatively low cost. The preferred vegetable oil is soy oil, although it is contemplated that other vegetable oils, such as rapeseed oil (also known as canola oil), cottonseed oil, and palm oil can be used in

30



ccordance with the present invention. Except for the preliminary blowing step where air is passed through the oil to remove impurities and to thicken it, the soy oil is otherwise unmodified. It does not require esterification as is required for some urethane products of the prior art. The preferred blown soy oil has the following composition:

100% Pure Soybean Oil Air Oxidized

Moisture	1.15 %
Free Fatty Acid	5.92 % as OLEIC
Phosphorous	55.5 ppm
Peroxide Value	137.22 Meq/Kg
Iron	6.5 ppm
Hydroxyl Number	212 mgKOH/g
Acid Value	12.46 mgKOH/g
Sulfur	200 ppm
Tin	< .5 ppm

Except for the use of the preferred unmodified, blown soy oil replacing the polyol, the preferred B-side reactant used to produce the foam of the invention is generally known in the art. Accordingly, preferred blowing agents for the invention are those that are likewise known in the art and may be chosen from the group comprising 134A HCFC, a hydrochlorofluorocarbon refrigerant available from Dow Chemical Co., Midland MI; methyl isobutyl ketone (MIBK); acetone; a hydrofluorocarbon; and methylene chloride. These preferred blowing agents create vapor bubbles in the reacting mass. Should other blowing agents be used that react chemically, such as water reacting with the isocyanate (NCO) groups, to produce a gaseous product, concentrations of other reactants may be adjusted to accommodate the reaction.

The cross-linking agents of the foam of the present invention are also those that are well known in the art. They must be at least di-functional (a diol). The preferred cross-linking agents for the foam of the invention are ethylene glycol and 1,4 butanediol; however, other diols may be used. It has been found that a mixture of ethylene glycol and 1,4 butanediol is particularly advantageous in the practice of the present invention. Ethylene glycol tends to offer a shorter chain molecular structure with many "dead end" sites, tending to create a firmer final foam resistant to tearing or "unzipping," while 1,4 butanediol offers a longer chain molecular structure, tending to create a softer foam.

Proper mixture of the two can create engineered foams of almost any desired structural characteristics.

5 In addition to the B-side's soy oil and blowing agent, one or more catalyst may be present. The preferred catalysts for the urethanes of the present invention are those that are generally known in the art and are most preferably tertiary amines chosen from the group comprising DABCO 33-LV® comprised of 33% 1,4 diaza-bicyclo-octane (triethylenediamine) and 67% dipropylene glycol, a gel catalyst available from the Air Products Corporation; DABCO® BL-22 blowing catalyst available from the Air Products Corporation; and POLYCAT® 41 trimerization catalyst available from the Air Products Corporation.

10 Also as known in the art, the B-side reactant may further comprise a silicone surfactant which functions to influence liquid surface tension and thereby influence the size of the bubbles formed and ultimately the size of the hardened void cells in the final foam product. This can effect foam density and foam rebound (index of elasticity of foam).

15 Also, the surfactant may function as a cell opening agent to cause larger cells to be formed in the foam. This results in uniform foam density, increased rebound, and a softer foam.

A molecular sieve may further be present to absorb excess water from the reaction mixture. The preferred molecular sieve of the present invention is available under the trade name L-paste™.

20 The flexible and semi-rigid foams of the invention will have greater than approximately 60% open cells. The preferred flexible foam of the invention will also have a density of from 1 lb. to 45 lb. per cubic foot and a hardness of durometer between 20 and 70 Shore "A."

25 The urethane foam of the present invention is produced by combining the A-side reactant with the B-side reactant in the same manner as is generally known in the art. Advantageously, use of the vegetable oil to replace the petroleum-based polyol does not require significant changes in the method of performing the reaction procedure. Upon combination of the A and B side reactants, an exothermic reaction ensues that may reach completion in anywhere from several minutes to several hours depending on the particular reactants and concentrations used. Typically, the reaction is carried out in a mold so that the foam expands to fill the mold, thereby creating a final foam product in the shape of the mold.

The components may be combined in differing amounts to yield differing results, as will be shown in the Examples presented in the detailed description below. Generally, however, the preferred flexible foam of the invention B-side mixture, when using the preferred components, is prepared with the following general weight ratios:

5	Blown soy oil	100 parts
	Cross-linking agent	8- 15 parts
	Blowing agent	8 - 15 parts
	Catalyst	1 - 12 parts

10 A petroleum based polyol such as polyether polyol, polyester polyol, or polyurea polyol may be substituted for some of the blown soy oil in the B-side of the reaction, however, this is not necessary. This preferred B-side formulation is then combined with the A-side to produce a foam. The preferred A-side, as discussed previously, is comprised of MDI or a prepolymer comprised of MDI and a vegetable oil, preferably soy oil. The A-  
15 side and B-side are typically, and preferably in an approximate ratio of about 35 parts to about 85 parts A-side to 100 parts B-side.

Flexible urethane foams may be produced with differing final qualities using the same vegetable oil by varying the particular other reactants chosen. For instance, it is expected that the use of relatively high molecular weight and high functionality isocyanates  
20 will result in a less flexible foam than will use of a lower molecular weight and lower functionality isocyanate when used with the same vegetable oil. Similarly, it is expected that lower molecular weight and lower functionality cross-linkers will result in a more flexible foam than will higher molecular weight and higher functionality cross-linkers when used with the same vegetable oil. Also, a ethylene glycol cross-linker will result in shorter  
25 final chains and a firmer foam, while use of a butanediol cross-linker results in longer chains and a softer foam. Moreover, it has been contemplated that chain extenders may also be employed in the present invention. Butanediol, in addition to acting as a cross-linker, may act as a chain extender.

Urethane elastomers can be produced in much the same manner as urethane foams, except that a blowing agent is not present to create void cells in the material. It has been  
30 discovered that useful urethane elastomers may be prepared using a vegetable oil to replace a petroleum-based polyester or polyether polyol. The preferred elastomer of the invention is produced using diphenylmethane diisocyanate (MDI); 1,4 butanediol cross-linking agent;

and a vegetable oil, preferably soy oil. A catalyst may be added to the reaction composition to decelerate the speed of the reaction. The preferred elastomer of the invention is prepared by combining the reactants. An exothermic reaction occurs that creates the elastomer. The preferred elastomer has an approximate density of 65 lb. to 75 lb. per cubic foot.

The following examples of preparation of foams and elastomers of the invention summarized in Table A will illustrate various embodiments of the invention. In the Examples, the B-Side (soy oil and other components), once blended, has a shelf life of several months. The A-side material in the following examples is comprised of modified diphenylmethane diisocyanate (MDI). The prepolymer A-side material in the following examples is the reaction product of a vegetable oil, preferably soy oil, and a modified diphenylmethane diisocyanate (MDI). There are four different MDI materials specified in the following examples; all are modified monomeric or polymeric diphenylmethane diisocyanates available from the Bayer Corp., Polymers Division, Rosemont IL: "Mondur® MA-2901" (Bayer Product Code No. C-1464); "Mondur®-448" (Bayer Product Code No. G-448), "Mondur® MRS-20", and "Mondur®-PF".

Also, "cure" in the following examples refers to the final, cured foam taken from the mold. The soy oil used in the following examples is blown soy oil obtained from Cargill, in Chicago, IL. Catalysts used include "DABCO 33-LV®," comprised of 33% 1,4-diaza-bicyclo-octane and 67% dipropylene glycol available from the Air Products Urethanes Division; "DABCO® BL-22," a tertiary amine blowing catalyst also available from the Air Products Urethanes Division; and "POLYCAT® 41" (n, n', n", dimethylamino-propyl-hexahydrotriazine tertiary amine) also available from the Air Products Urethanes Division.

Catalysts in the following Examples may be referred to as "front end," "back end," and "blowing". Front end catalysts tend to speed the early portion of the reaction, while back end catalysts tend to speed the later, curing portion of the reaction. A blowing catalyst effects the timing of the activation of the blowing agent. Some of the Examples include "L-paste™," which is a trade name for a molecular sieve for absorbing water. Some also contain "DABCO® DC-5160," a silicone surfactant available from Air Products Urethane Division.

## Examples

### Example 1

5           The B-side material was prepared as follows:

- 50 g Soy Oil
- 5 g Ethylene Glycol (cross-linker)
- 1 g Front end catalyst (DABCO 33-LV®;  
33 % triethylenediamine and  
10       67 % dipropylene glycol)
- 1 g Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)
- 4 g Methyl Isobutyl Ketone (blowing agent)

15           Blown soy oil has a molecular weight of about 278, while the ethylene glycol has a  
molecular weight of about 62. Thus, the molar ratio of ethylene glycol to blown soy oil is  
0.22:1. Since the ethylene glycol has two hydroxyl (OH) groups with which to cross-link  
the constituent fatty acids of the blown soy oil, the molar ratio of the hydroxyl (OH) groups  
of the ethylene glycol to soy oil is about 0.45:1. The resulting B-side was then combined  
with an A-side material in a ratio of 50 parts A-side to 100 parts B-side. The A-side  
20       material is comprised of Mondur® 448, a modified monomeric diphenylmethane  
diisocyanate (pMDI). The cure was acceptable; however, the cellular material remained  
tacky at the surface for 20 minutes.

### Example 2

25           The B-side is the same as that of Example 1. The A-side is comprised of MA-2901,  
a modified diphenylmethane diisocyanate. The B-side was combined with the A-side in a  
ratio of 52 parts A-side to 100 parts B-side. The cure was acceptable, although the cellular  
material remained tacky for 12 minutes.

Example 3

The A-side was the same as Example 2. The B-side was again the same as that of Example 1, except that 1.5 parts of methanol were added as additional blowing agent. The ratio was 52 parts A-side to 100 parts B-side. The sample cured in 1 hour. It was not a favorable result in that the cellular material foamed and then fell back to solid and rose again. The methanol apparently had an adverse affect.

Example 4

B-side: 100 g Soy Oil  
5 g Ethylene Glycol (cross-linker)  
2.5 g Front end catalyst (DABCO 33-LV®;  
33 % 1,4-diaza-bicyclo-octane and  
67 % dipropylene glycol)  
2.5 g Blow catalyst (DABCO® BL-22; a tertiary amine  
catalyst)  
4 g Methyl Isobutyl Ketone (MIBK)

The A-side was the same as Example 2. The materials were reacted in a ratio of 50 parts A-side to 100 parts B-side. The results were a good foam, but weak in tensile strength.

Example 5

The B-side and A-side are the same as in Example 4. However, the materials were reacted in a ratio of 52 parts A-side to 100 parts B-side. The results were essentially the same as in Example 4 with a little better tensile strength.

Example 6

B-Side: 103 g Soy Oil  
10 g Ethylene Glycol (cross-linker)  
11 g Acetone (Blowing agent)  
2.5 g Front end catalyst (DABCO 33-LV®;  
33 % 1,4-diaza-bicyclo-octane and  
67 % dipropylene glycol)

2.5 g Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)

The molar ratio of ethylene glycol to blown soy oil is 0.44:1. With two hydroxyl (OH) groups with which to cross-link the constituent fatty acids of the blown soy oil, the molar ratio of the hydroxyl (OH) groups of the ethylene glycol to soy oil is about 0.90:1. The A-side comprises 52 parts MA-2901, a modified monomeric diphenylmethane diisocyanate, to 100 parts B-side. The resulting foam was hard and its cell size large. It fell back to a solid, largely due to too much blowing agent.

#### Example 7

B-side: 100 g Soy Oil  
8 g Ethylene Glycol (cross-linker)  
5 g Acetone (Blowing agent)  
2.5 g Front end catalyst (DABCO 33-LV®;  
33 % 1,4-diaza-bicyclo-octane and  
67 % dipropylene glycol)  
2.5 g Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)

The molar ratio of ethylene glycol to blown soy oil is 0.35 to 1. With two hydroxyl (OH) groups with which to cross-link the constituent fatty acids of the blown soy oil, the molar ratio of the hydroxyl (OH) groups of the ethylene glycol to soy oil is about 0.70:1. The A-side comprises MA-2901, a modified monomeric diphenylmethane diisocyanate, and is present in 51 parts A-side to 100 parts B-side. The resulting foam is a generally good foam, having low tensile strength but a better density range.

#### Example 8

The B-side is the same as that of Example 7. The A-side also comprises MA-2901, a modified monomeric diphenylmethane diisocyanate, as in Example 7. The A-side is present in a ratio of 45 parts A-side to 100 parts B-side.

Example 9

The A-side and B-side are the same as in Example 7. However, 72 parts A-side were reacted with 100 parts B-side. The resulting foam fell back and did not cure after 1 hour, indicating an overcharge of A-side.

Example 10

B-side	100 g	Soy Oil
	11 g	Ethylene Glycol (cross-linker)
	4 g	Methyl Isobutyl Ketone (MIBK)
	3 g	Front end catalyst (DABCO 33-LV®; 33 % 1,4-diaza-bicyclo-octane and 67 % dipropylene glycol)
	3 g	Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)

The molar ratio of ethylene glycol to blown soy oil is 0.49:1. With two hydroxyl (OH) groups with which to cross-link the constituent fatty acids of the blown soy oil, the molar ratio of the hydroxyl (OH) groups of the ethylene glycol to soy oil is about 0.99:1. The A-side comprised MA-2901, a modified monomeric diphenylmethane diisocyanate. The A-side was reacted with the B-side in a ratio of 50 parts A-side to 100 parts B-side. The resulting foam had a 15 minute cure and a very slow recovery. However, the final cure was insufficient because it did not occur for 72 hours.

Example 11

B-side	100 g	Soy Oil
	11 g	Ethylene Glycol (cross-linker)
	4 g	Methyl Isobutyl Ketone (MIBK)
	3 g	Front end catalyst (DABCO 33-LV®; 33 % 1,4-diaza-bicyclo-octane and 67 % dipropylene glycol)
	3 g	Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)



The B-side is as in Example 10. The A-side comprises Mondur® 448, a modified monomeric diphenylmethane diisocyanate, in a ratio of 50 parts A-side to 100 parts B-side. The resulting foam cures in 15 minutes, but is very crumbly.

#### Example 12

B-side	100 g Soy Oil
	11 g Ethylene Glycol (cross-linker)
	4 g Methyl Isobutyl Ketone (MIBK)
	3 g front end catalyst (DABCO 33-LV®;
	33 % diaza-bicyclo-octane and
	67 % dipropylene glycol)
	3 g Blow catalyst (DABCO® BL-22; a tertiary amine
	catalyst)

The B-side is as in Example 10. The A-side comprised 76 parts MA-2901, a modified monomeric diphenylmethane diisocyanate, to 100 parts B-side. The resulting foam cures in 30 minutes, but has a very fast, complete fall back.

#### Example 13

B-side	100 g Soy Oil
	5 g Ethylene Glycol (cross-linker)
	5 g 1,4 butanediol (cross-linker)
	4 g Methyl Isobutyl Ketone (MIBK)
	2.5 g Front end catalyst (DABCO 33-LV®;
	33 % 1,4-diaza-bicyclo-octane and
	67 % dipropylene glycol)
	2.5 g Blow catalyst (DABCO® BL-22; a tertiary amine
	catalyst)

Ethylene glycol has a molecular weight of about 62 and 1,4 butanediol has a molecular weight of about 90. Thus, the molar ratio of the ethylene glycol to blown soy oil is 0.22:1 and the molar ratio of the 1,4 butanediol to blown soy oil is 0.15:1. Since each of the ethylene glycol and 1,4 butanediol have two hydroxyl (OH) groups with which to cross-link the constituent fatty acids of the blown soy oil, the molar ratio of the hydroxyl (OH) groups of the 50/50 ethylene glycol/1,4 butanediol cross-linker mixture to the blown soy oil is about 0.75:1. The A-side was reacted at 74 parts MA-2901, a modified monomeric

diphenylmethane diisocyanate to 100 parts B-side. The resulting foam cured to the touch within 3 minutes and fully cured within 15 minutes. It has good properties.

### Example 14

B-side

100 g	Soy Oil
5 g	Ethylene Glycol (cross-linker)
5 g	1,4 butanediol (cross-linker)
4 g	Methyl Isobutyl Ketone (MIBK)
2.5 g	Front end catalyst (DABCO 33-LV®; 33 % 1,4-diaza-bicyclo-octane and 67 % dipropylene glycol)
2.5 g	Back end catalyst (POLYCAT® 41; n, n', n'', dimethylamino-propyl- hexahydrotriazine tertiary amine)
2 g	Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)

The A-side was reacted at 74 parts, a modified MDI, MA-2901, to 100 parts B-side. The resulting foam cured to the touch within 3 minutes and exhibited slightly better initial strength than the foam of Example 13. It fully cured within 15 minutes with good properties.

### Example 15

B-side

- 200 g Soy Oil
- 7 g Ethylene Glycol (cross-linker)
- 16 g 1,4 butanediol (cross linker)
- 2.5 g Front end catalyst (DABCO 33-LV®;  
33 % 1,4-diaza-bicyclo-octane and  
67 % dipropylene glycol)
- 2.5 g Blow catalyst (DABCO® BL-22' a tertiary amine  
catalyst)
- 2 g Back end catalyst (POLYCAT® 41;  
n, n', n'', dimethylamino-propyl-  
hexahydrotriazine tertiary amine)

The molar ratio of the ethylene glycol to blown soy oil is 0.15:1 and the molar ratio of the 1,4 butanediol to blown soy oil is 0.24:1. Since each of the ethylene glycol and 1,4 butanediol have two hydroxyl (OH) groups with which to cross-link the constituent fatty

acids of the blown soy oil, the molar ratio of the hydroxyl (OH) groups of the 50/50 ethylene glycol/1,4 butanediol cross-linker mixture to blown soy oil is about 0.80:1.

The A-side was reacted at 74 parts, a modified MDI, MA-2901 to 100 parts B-side. The resulting foam had very good qualities. The foam exhibited good elastomeric and fast cure (tack-free after 90 seconds) properties and was soft with good elastomeric properties after 1 hour.

#### Example 16

The B-side is the same blend as Example 15. The A-side comprises, a modified MDI, Mondur® 448. The A-side was reacted at 74 parts A-side to 100 parts B-side. The reaction time was good and the resulting foam was a stiff flexible foam with good elastomeric properties. The foam continued to exhibit good elastomeric properties after 1 hour.

#### Example 17

B-side	100 g Soy Oil
	5 g Ethylene Glycol (cross-linker)
	5 g 1,4 butanediol (cross-linker)
	2.5 g Front end catalyst (DABCO 33-LV®;
	33 % 1,4-diaza-bicyclo-octane and
	67 % dipropylene glycol)
	2 g Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)
	2 g Back end catalyst (POLYCAT® 41;
	n, n', n'', dimethylamino-propyl-hexahydrotriazine tertiary amine)
	2 g Molecular sieve (L-paste™)

The molar ratio of the hydroxyl (OH) groups of the 50/50 ethylene glycol/1,4 butanediol cross-linker mixture to soy oil is again about 0.75:1.

The A-side comprises a 50/50 blend of, a modified MDI, MA-2901 and a modified pMDI, Mondur® 448. The A-side was reacted with the B-side at 74 parts A-side to 100 parts B-side. The resulting foam is a good foam with good flexibility, high density, but still needs tensile improvements.

Example 18

	B-side	200 g Soy Oil
		5 g Ethylene Glycol (cross-linker)
5		21 g 1,4 butanediol (cross-linker)
		5 g Front end catalyst (DABCO 33-LV®; 33 % 1,4-diaza-bicyclo-octane and 67 % dipropylene glycol)
10		5 g Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)
		2 g Back end catalyst (POLYCAT® 41; n, n', n'', dimethylamino-propyl- hexahydrotriazine tertiary amine)
15		6 g Molecular sieve (L-paste™)

The molar ratio of the hydroxyl (OH) groups of the 5/21 ethylene glycol/1,4 butanediol mixture to blown soy oil is about 0.85:1.

The A-side comprises a 50/50 blend of a modified MDI, MA-2901 and a modified pMDI, Mondur® 448. The A-side was reacted with the B-side at 74 parts A-side to 100 parts B-side. The resulting foam is very similar to that of Example 17 and is a good foam with good flexibility, high density, but still needs tensile improvements.

Example 19

25	B-side	200 g Soy Oil
		22 g Ethylene Glycol (cross-linker)
		4 g 1,4 butanediol (cross-linker)
		2.5 g Front end catalyst (DABCO 33-LV®; 33 % 1,4-diaza-bicyclo-octane and 67 % dipropylene glycol)
30		2.5 g Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)
		5 g Back end catalyst (POLYCAT 41®; n, n', n'', dimethylamino-propyl- hexahydrotriazine tertiary amine)
35		16 g Molecular sieve (L-paste™)
		4 g Silicone surfactants (DABCO® DC-5160)

The molar ratio of the hydroxyl (OH) groups of the 22/4 ethylene glycol/1,4 butanediol mixture to blown soy oil is about 1.10:1. The A-side comprises a modified MDI, MA-290. The A-side and the B-side were reacted at 74 parts A-side to 100 parts B-

side. The resulting foam demonstrated very good properties. It is almost a solid elastomer with good rebound.

#### Example 20

5                    B-side        200 g Soy Oil  
                                  22 g Ethylene Glycol (cross-linker)  
                                  4 g 1,4 butanediol (cross-linker)  
                                  10 g Methylene Chloride (blowing agent)  
 10                            2.5 g Front end catalyst (DABCO 33-LV®;  
    33 % 1,4-diaza-bicyclo-octane and  
    67 % dipropylene glycol)  
                                  2.5 g Blow catalyst (DABCO® BL-22; a tertiary amine  
    catalyst)  
 15                            5 g Back end catalyst (POLYCAT® 41;  
    n, n', n'', dimethylamino-propyl-  
    hexahydrotriazine tertiary amine)  
                                  16 g Molecular sieve (L-paste™)  
                                  4 g Silicone surfactants (DABCO® DC-5160)

20                    The molar ratio of the hydroxyl (OH) groups of the 22/4 ethylene glycol/1,4  
 butanediol mixture to blown soy oil is again about 1.10:1. The A-side comprises a  
 modified MDI, MA-2901, and was reacted at 74 parts A-side to 100 parts B-side. The  
 resulting foam was a very good foam having uniform cell size, good flex, moderate density,  
 good rebound and higher tensile strength.

#### Example 21

                         B-side        200 g Soy Oil  
                                  22 g Ethylene Glycol (cross-linker)  
 30                            4 g 1,4 butanediol (cross-linker)  
                                  10 g Methylene Chloride (blowing agent)  
                                  2.5 g Front end catalyst (DABCO 33-LV®;  
    33 % 1,4-diaza-bicyclo-octane and  
    67 % dipropylene glycol)  
 35                            2.5 g Blow catalyst (DABCO® BL-22; a tertiary amine  
    catalyst)  
                                  5 g Back end catalyst (POLYCAT 41®;  
    n, n', n'', dimethylamino-propyl-  
    hexahydrotriazine tertiary amine)  
 40                            16 g Molecular sieve (L-paste™)  
                                  4 g Silicone surfactants (DABCO® DC-5160)  
                                  2 g Green pigment

The molar ratio of the hydroxyl (OH) groups of the 22/4 ethylene glycol/1,4 butanediol mixture to blown soy oil is again about 1.10:1. The A-side comprises a modified MDI, MA-2901, and was reacted at 81 parts A-side to 100 parts B-side.

### Example 22

B-side	200 g Soy Oil
	22 g Ethylene Glycol (cross-linker)
	4 g 1,4 butanediol (cross-linker)
	12 g Methylene Chloride (blowing agent)
	2.5 g Front end catalyst (DABCO 33-LV®; 33 % 1,4-diaza-bicyclo-octane and 67 % dipropylene glycol)
	2.5 g Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)
	5 g Back end catalyst (POLYCAT 41®; n, n', n'', dimethylamino-propyl- hexahydrotriazine tertiary amine)
	16 g Molecular sieve (L-paste™)
	4 g Silicone surfactants (DABCO® DC-5160)
	2 g Green pigment

The molar ratio of the hydroxyl (OH) groups of the 22/4 ethylene glycol/1,4 butanediol mixture to blown soy oil is again about 1.10:1. The A-side comprises a modified MDI, MA-2901. The A-side and the B-side were reacted at 80 parts A-side to 100 parts B-side. The resulting foam was a good foam. It was a stiffer flexible foam with good cell size, good uniformity, and low to moderate density.

### Example 23

B-side	400 g Soy Oil
	35 g Ethylene Glycol (cross-linker)
	15 g 1,4 butanediol (cross-linker)
	24 g Methylene Chloride (blowing agent)
	5 g Front end catalyst (DABCO 33-LV®; 33 % 1,4-diaza-bicyclo-octane and 67 % dipropylene glycol)
	5 g Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)
	9 g Back end catalyst (POLYCAT® 41; n, n', n'', dimethylamino-propyl- hexahydrotriazine tertiary amine)

32 g Molecular sieve (L-paste™)  
12.5 g Silicone surfactants (DABCO® DC-5160)  
4 g Green pigment

5        The molar ratio of the hydroxyl (OH) groups of the 35/15 ethylene glycol/1,4 butanediol mixture to blown soy oil is about 1.00:1. The A-side comprises a modified MDI, MA-2901, and was reacted at 74 parts A-side to 100 parts B-side. The resulting foam is low in density with poor tensile strength.

10        Example 24

B-side	235 g Soy Oil
	25 g Ethylene Glycol (cross-linker)
	6 g 1,4 butanediol (cross-linker)
15	12 g Methylene Chloride (blowing agent)
	2 g Front end catalyst (DABCO 33-LV®;
	33 % 1,4-diaza-bicyclo-octane and
	67 % dipropylene glycol)
20	2 g Blow catalyst (DABCO® BL-22; a tertiary amine catalyst)
	1.75 g Back end catalyst (POLYCAT 41®;
	n, n', n'', dimethylamino-propyl-
	hexahydrotriazine tertiary amine)
25	25 g Molecular sieve (L-paste™)

25        The molar ratio of the hydroxyl (OH) groups of the 25/6 ethylene glycol/1,4 butanediol mixture to soy oil is about 1.50:1. The A-side comprises a 2,4' rich polymeric MDI, Mondur® MRS-20, and was reacted at 70 parts to 100 parts B-side. The resulting reaction had no foaming and no real reaction.

30        Example 25

35        Example 24 is repeated with A-side comprising Mondur®-PF, a modified MDI. Again, no foaming and not a good reaction.

Example 26

Example 24 is again repeated, with the A-side this time comprising a 50/50 mixture of a modified MDI, MA-2901, and a modified pMDI, Mondur® 448. It is reacted at 70 parts to 100 parts B-side.

Example 27

The A-side comprises a modified MDI, MA-2901. The B-side comprises the following:

B-side	100 g	Soy Oil
	7 g	Dipropylene-glycol (cross-linker)
	2 g	Front end catalyst (DABCO 33-LV®;
		33 % triethylenediamine and
		67 % dipropylene glycol)
	2 g	Back end catalyst (DABCO® 8154; an amine salt)

The A-side and B-side reactions were mixed in a ratio of 60 parts A-side to 100 parts B-side. The resultant foam exhibited excellent properties.

Example 28

B-side	100 g	Soy Oil
	3 g	Dipropylene glycol (cross-linker)
	2 g	Surfactant
	2 g	Front end catalyst (DABCO 33-LV®;
		33 % triethylenediamine and
		67 % dipropylene glycol)
	2 g	Back end catalyst (DABCO® 8154; an amine salt)

The A-side and B-side reactions were mixed in a ratio of 60 parts A-side to 100 parts B-side. The resultant reaction produced a foam exhibiting excellent properties.

Example 29

The A-side and B-side components are identical to those in Example 28. The A-side was reacted with the B-side in a ratio of 68 parts A-side and 100 parts B-side. Once again, the foam produced by the reaction had excellent properties.



Example 30

The A-side comprises a mix of a modified MDI, MA-2901, and a modified pMDI, Mondur® 448. The B-side comprises the following:

5                    B-side            100 g Soy Oil  
                                 3 g Tripropylene glycol (cross-linker)  
                                 3 g Dipropylene glycol (cross-linker)  
                                 2 g Front end catalyst (DABCO 33-LV®;  
10                                33 % triethylenediamine and  
                                 67 % dipropylene glycol).  
                                 2 g Back end catalyst (DABCO® 8154; an amine salt)

The A-side and B-side were mixed in a ratio of 60 parts A-side to 100 parts B-side. The resultant foam was a rigid foam exhibiting excellent properties.

Example 31

In this example, the A-side was identical to the A-side of Example 30 and the B-side is identical to Example 30 except for the fact that 6% butanediol was added to the B-side.

20    The A-side and B-side were mixed in a ratio of 60 parts A-side to 100 parts B-side. The resultant foam was a rigid foam exhibiting excellent properties. The addition of the butanediol increased the speed of the reaction compared to Example 30.

Example 32

25                    The A-side comprises polymeric MDI. The B-side comprises the following:

                         B-side            200 g Soy Oil  
                                 30 g Ethylene glycol (cross-linker)  
                                 15 g Butanediol (cross-linker)  
30                                5 g Aliphatic amine tetrol (CL-485; cross-linker)  
                                 25 g Molecular sieve (L-paste™)  
                                 8 g Front end catalyst (DABCO 33-LV®;  
                                 33 % triethylenediamine and  
                                 67 % dipropylene glycol)  
35                                5 g Back end catalyst (DABCO® 1854; an amine salt)

The A-side and B-side were mixed in a 1:1 ratio. The foam resulting from the chemical reaction was a rigid foam with good properties.

Example 33

B-side      100 g Soy Oil  
              10 g Butanediol (cross-linker)  
5             6.4 g Ethylene glycol (cross-linker).  
              3 g Aliphatic amine tetrol (cross-linker)  
              3.2 g Front end catalyst (DABCO 33-LV®;  
                  33 % triethylenediamine and  
                  67 % dipropylene glycol)  
10            3.0 g Back end catalyst (DABCO® 1854; an amine salt)  
              5 % Molecular sieve (L-paste™)

The A-side and B-side were mixed in a ratio of 35 parts A-side to 100 parts B-side.

The resulting foam was very good after about 15 minutes.

Example 34

The A-side comprises either MDI or pMDI. The B-side comprised the following:

B-side      200 g Soy Oil  
              200 g Polyurea polyol  
20            48 g Aliphatic amine tetrol (cross-linker)  
              30 g Ethylene glycol (cross-linker)  
              3 g Front end catalyst (DABCO 33-LV®;  
                  33 % triethylenediamine and  
                  67 % dipropylene glycol)  
25            3 g Back end catalyst (Polycat 41®;  
                  n, n', n'', dimethylamino-propyl-  
                  hexahydrotriazine tertiary amine)  
              3 g Tertiary amine catalyst (DABCO® BL-22)  
30            7 g Molecular sieve (L-paste™)

The A-side and B-side were combined in a ratio of 50 parts A-side to 100 parts B-side. The result reaction occurred very fast and the resultant elastomer exhibited good properties. Combining the A-side and the B-side in a ratio of 68 parts A-side to 100 parts B-side also results in an elastomer with good properties.

#### Example 35

B-side	300 g Soy Oil
	300 g Polyurea polyol (petroleum based polyol)
	33 g Butanediol (cross-linker)
	11.3 g Front end catalyst (DABCO 33-LV®;
	33 % triethylenediamine and
	67 % dipropylene glycol)
	7.6 g Back end catalyst (Polycat® 41;
	n, n', n", dimethylamino-propyl-
	hexahydrotriazine tertiary amine
	5 g Aliphatic amine tetrol (DABCO® CL-485; cross-
	linker)

The A-side was blended with the B-side in a ratio of 40 parts A-side to 100 parts B-side. The resultant foam had good properties, but was slightly hard.

#### Example 36

The A-side and B-side are identical to Example 35, however, 5 % methylene chloride and 1 % of a stabilizing anti-oxidant, Stabaxol® were added to the B-side. The A-side and the B-side were mixed in a ratio of 32 parts A-side to 100 parts B-side and a ratio of 36.5 parts A-side to 100 parts B-side. Both resulting foams were good, soft foams. The addition of the methylene chloride as a blowing agent greatly assisted the reaction without pulling out water thereby allowing the foam to stay soft.

#### Example 37

The A-side comprises an 50/50 mixture of modified MDI and modified pMDI. The B-side comprises the following:

B-side	400 g Soy Oil
	400 g Polyurea polyol (petroleum based polyol)

96 g Aliphatic amine tetrol (cross-linker; amine salt)  
 60 g Ethylene glycol (cross-linker)  
 6 g Front end catalyst (DABCO 33-LV®;  
 33 % triethylenediamine and  
 67 % dipropylene glycol)  
 3 g Back end catalyst (tertiary amine catalyst)  
 6 g Blow catalyst (DABCO® BL-22)

The A-side was combined with the B-side in a ratio of 50 parts A-side to 100 parts B-side. The resultant foam exhibited good overall properties.

### Example 38

The A-side comprises a polymeric MDI, Mondur® MR light. The B-side comprises the following:

B-side	50 g	Soy Oil
	50 g	Sucrose polyol (Bayer 4035)
	10 g	Ethylene glycol (cross-linker)
	2.5 g	Dipropylene glycol (cross-linker)
	3.0 g	Front end catalyst
	2.0 g	Back end catalyst (tertiary block amine catalyst)

The A-side was mixed with the B-side at the following ratios:

<u>A-side</u>	<u>B-side</u>
50	100
70	100
80	100
90	100
100	100

Each mix ratio resulted in a very fast reacting high density foam exhibiting good qualities overall.

The above description is considered that of the preferred embodiments only. Modifications of the invention will occur to those skilled in the art and to those who make or use the invention. Therefore, it is understood that the embodiments shown in the drawings and described above are merely for illustrative purposes and not intended to limit the scope of the invention, which is defined by the following claims as interpreted according to the principles of patent law, including the doctrine of equivalents.

What is claimed is:

1. A cellular material comprising the reaction product of an A-side and a B-side, wherein said A-side is comprised of a diisocyanate and said B-side comprises a vegetable oil, a cross-linking agent comprised of a multi-functional alcohol and a catalyst.

2. The cellular material of claim 1, wherein said B-side further includes a blowing agent.

3. The cellular material of claim 1, wherein said vegetable oil is chosen from the group comprising soy oil, rapeseed oil, cottonseed oil, or palm oil.

4. The cellular material of claim 1, wherein said vegetable oil comprises blown soy oil.

5. The cellular material of claim 1, wherein said catalyst is a tertiary amine.

6. The cellular material of claim 1, wherein said multi-functional alcohol is present in a ratio to said vegetable oil such that there are at least 0.7 moles of hydroxyl (OH) groups per mole of vegetable oil.

7. The cellular material of claim 1, wherein said diisocyanate is selected from the group consisting of 2,4 diisocyanate, 4,4' diphenylmethane diisocyanate, and 2,4 diphenylmethane diisocyanate.

8. The cellular material of claim 2, wherein said B-side further comprises a surfactant.

9. The cellular material of claim 1, wherein said diisocyanate is a mixture of at least two diisocyanates.

10. The cellular material of claim 9, wherein said diisocyanate is a mixture of at least two diisocyanates selected from the group comprising 2,4 diisocyanate, 4,4' diphenylmethane diisocyanate and 2,4 diphenylmethane diisocyanate.

5 11. The cellular material of claim 2, wherein said blowing agent is selected from the group comprising water, acetone, methyl isobutyl ketone, methylene chloride, a hydrochlorofluorocarbon, or a hydrofluorocarbon.

10 12. The cellular material of claim 1, wherein said cross-linker is selected from the group comprising ethylene glycol, 1,4 butanediol, and dipropylene glycol.

13. The cellular material of claim 1, wherein said cross-linker is a combination of ethylene glycol and 1,4 butanediol.

15 14. The cellular material of claim 1, wherein the B-side further comprises a petroleum-based polyol.

15. The cellular material of claim 14, wherein said petroleum-based polyol comprises a polyurea polyol.

20 16. The cellular material comprising the reactive product of an A-side comprised of a prepolymer diisocyanate and a B-side, wherein said B-side comprises a first vegetable oil, a cross-linking agent comprised of a multi-functional alcohol, a catalyst, and a blowing agent.

25 17. The cellular material of claim 16, wherein the prepolymer diisocyanate comprises the reaction product of a diisocyanate and a second vegetable oil.

30 18. The cellular material of claim 17, wherein said first vegetable oil and said second vegetable oil are selected from the group comprising soy oil, rapeseed, cottonseed oil, or palm oil.

19. The cellular material of claim 17, wherein said first vegetable oil and said second vegetable oil comprise blown soy oil.

20. The cellular material of claim 16, wherein said catalyst is a tertiary amine.

21. The cellular material of claim 16, wherein said multi-functional alcohol is present in a ratio to said second vegetable oil such that there are at least 0.7 moles of hydroxyl (OH) groups per mole of said second vegetable oil.

22. The cellular material of claim 17, wherein said diisocyanate comprises diphenylmethane diisocyanate (MDI).

23. The cellular material of claim 18, wherein the B-side further comprises a petroleum-based polyol.

24. The cellular material of claim 23, wherein said petroleum-based polyol comprises a polyurea polyol.

25. A method of preparing a cellular material comprising the steps of combining an A-side material with a B-side material, wherein said A-side comprises a diisocyanate and said B-side material comprises a vegetable oil, a cross-linker comprised of a multi-functional alcohol, a catalyst, and a blowing agent.

26. The method of claim 25, wherein said vegetable oil is chosen from the group comprising soy oil, rapeseed oil, cottonseed oil, or palm oil.

27. The method of claim 25, wherein said vegetable oil comprises blown soy oil.

28. The method of claim 25, wherein said catalyst is a tertiary amine.

29. The method of claim 25, wherein said multi-functional alcohol is present in a ratio with said vegetable oil such that there is at least 0.7 moles of hydroxyl (OH) groups per mole of vegetable oil.

5 30. The method of claim 25, wherein said B-side further comprises a petroleum-based polyol.

31. The method of claim 26, wherein said petroleum-based polyol comprises a polyurea polyol.

10 32. A method of preparing a cellular material comprising the steps of combining an A-side material with a B-side material, wherein said A-side comprises a prepolymer diisocyanate and a B-side, wherein said B-side comprises a first vegetable oil, a cross-linking agent comprised of a multi-functional alcohol, a catalyst, and a blowing agent.

15 33. The method of claim 32, wherein the prepolymer diisocyanate comprises the reaction product of a diisocyanate and a second vegetable oil.

20 34. The method of claim 33, where in said first vegetable oil and said second vegetable oil are selected from the group comprising soy oil, rapeseed, cottonseed oil, or palm oil.

35. The method of claim 33, wherein said first vegetable oil and said second vegetable oil comprise blown soy oil.

25 36. The method of claim 32, wherein said catalyst is a tertiary amine.

37. The method of claim 32, wherein said multi-functional alcohol is present in a ratio to said second vegetable oil such that there are at least 0.7 moles of hydroxyl (OH) groups per mole of said second vegetable oil.

30 38. The method of claim 33, wherein said diisocyanate comprises diphenylmethane diisocyanate (MDI).



39. The method of claim 32, wherein the B-side further comprises a petroleum-based polyol.

40. The method of claim 39, wherein said petroleum-based polyol comprises a polyurea polyol.

41. A method of selectively preparing cellular materials of varied physical properties comprising the steps of reacting an A-side material with a B-side material, wherein said A-side comprises an isocyanate and said B-side material comprises blown soy oil, a multi-functional alcohol cross-linking agent present in such quantities that a ratio of moles of hydroxyl (OH) groups to moles of soy oil is between 0.7 and 1.2 equivalent moles of hydroxyl (OH) groups to one mole of soy oil, a tertiary amine catalyst, and a blowing agent, wherein the varied foam physical properties being obtained by the selection and proportions of the blowing agents, cross-linkers, catalysts, and isocyanates.

42. The method of preparing a cellular material as in claim 41, wherein the multi-functional alcohol cross-linking agent comprises a blend of ethylene glycol and 1,4-butanediol, the varied foam physical properties being obtained by selection of the proportions of said cross-linking agents.

43. The method of preparing a cellular material as in claim 41, wherein the blowing agent is selected from the group consisting of methyl isobutyl ketone, acetone, and methylene chloride.

44. The method of preparing a cellular material as in claim 41, wherein the ratio of the A-side to the B-side is 35 to 85 parts to 100 parts.

45. A polyurethane cellular plastic comprising the reaction product of an A-side and a B-side, wherein said A-side comprises an diisocyanate and said B-side is comprised of soy oil, a cross-linking agent comprised of a multi-functional alcohol present in a ratio to said soy oil such that there are at least 0.7 moles of hydroxyl (OH) groups per mole of soy oil, a catalyst, and a blowing agent.

46. The polyurethane cellular plastic of claim 45, wherein the multi-functional alcohol is present in a ratio to said soy oil such that there are between 0.7 to 1.2 moles hydroxyl (OH) groups per mole of soy oil, said catalyst is present in the amount of at least 2.5 parts and said isocyanate is present in the amount of 35 parts per 100 parts of the B-side.

47. A cellular plastic foam material, comprising the reaction product of between 35 and 85 parts of an A-side material and 100 parts of a B-side material, wherein said A-side material comprises an isocyanate and said B-side material comprises 100 parts of blown soy oil, between 8 to 18 parts cross-linking agent providing at least 0.7 moles of OH groups per mole of vegetable oil, 1 to 12 parts catalyst and 2 to 14 parts blowing agent.

48. A cellular plastic foam material, comprising the reaction product of 35 to 85 parts of an A-side material and 100 parts of a B-side material, wherein said A-side material comprises an isocyanate and said B-side material comprises 100 parts blown soy oil, from 8 to 16 parts cross-linking agent providing 0.70 to 1.2 moles OH per mole soy oil, from 2.5 to 11 parts catalyst and from 5 to 13 parts blowing agent.

49. A cellular plastic foam material comprising the reaction product of 35 to 85 parts of an A-side material with 100 parts of a B-side material, wherein said A-side comprises an isocyanate and said B-side comprises 100 parts blown soy oil, from 9 to 14 parts cross-linking agent providing 0.70 to 1.2 moles OH per mole soy oil, from 2 to 6 parts catalyst and from 4 to 9 parts blowing agent.

50. The cellular plastic foam material of claim 49, wherein said foam has at least 60% open cells.

51. The cellular plastic foam material of claim 49, wherein said cellular plastic foam material has a density of between approximately 65 lb. to 1.5 lb. per cubic foot.

52. The cellular plastic foam material of claim 49, wherein said catalyst comprises a tertiary amine.

53. The cellular plastic foam material of claim 49, wherein said catalyst comprises a mixture of a front end catalyst and a back end catalyst.

54. The cellular plastic foam material of claim 49, wherein said catalyst is chosen from the group comprising a mixture of 33% 1,4-diaza-bicyclo-octane and 67% dipropylene glycol; a tertiary amine blowing catalyst, and n, n', n'', dimethylamino-propyl-hexahydrotriazine tertiary amine.

55. The cellular plastic foam material of claim 49, wherein said cross-linker is chosen from the group comprising ethylene glycol and 1,4 butanediol.

56. The cellular plastic foam material of claim 49, wherein said cross-linker comprises a mixture of 1,4 butanediol and ethylene glycol.

57. The cellular plastic foam material of claim 49, wherein said blowing agent is chosen from the group comprising water, acetone, methyl isobutyl ketone, methylene chloride, a hydrochlorofluorocarbon, and a hydrofluorocarbon.

58. The cellular plastic foam material of claim 49, wherein said isocyanate is chosen from the group consisting of 2,4 diisocyanate, 4,4' diphenylmethane diisocyanate, and 2,4 diphenylmethane diisocyanate.

59. The cellular plastic foam material of claim 49, wherein said B-side material further comprises from 2-5 parts surfactant agent for effecting foam cell size.

60. The cellular plastic foam material of claim 49, wherein said B-side material further comprises a molecular sieve agent for absorbing water.

61. A solid plastic elastomer comprising the reaction product of 35 to 85 parts of an A-side material and 100 parts of a B-side material, wherein said A-side material comprises an isocyanate and said B-side material comprises 100 parts blown soy oil, 8 to 20 parts cross-linking agent, and from 1 to 15 parts catalyst.

## AMENDED CLAIMS

[received by the International Bureau on 15 February 2000 (15.02.00);  
original claims 1 to 61 unchanged; new claims 62 to 65 added (1 page )]

62. A cellular material comprising the reaction product of an A-side and a B-side,  
wherein said A-side is comprised of a diisocyanate and said B-side comprises a vegetable  
oil, a cross-linking agent comprised of a multi-functional alcohol and a catalyst, wherein  
said vegetable oil and said cross-linking agent are substantially non-esterfied prior to said  
5 A-side reacting with said B-side.

63. The cellular material comprising the reactive product of an A-side comprised of a  
prepolymer diisocyanate and a B-side, wherein the B-side comprises a first vegetable oil, a  
cross-linking agent comprised of a multi-functional alcohol, a catalyst, and a blowing agent,  
10 wherein said first vegetable oil, said cross-linking agent, and said blowing agent are  
substantially non-esterfied prior to said A-side reacting with said B-side.

64. A method of preparing a cellular material comprising the steps of combining an A-  
side material with a B-side material, wherein said A-side comprises a diisocyanate and said  
15 B-side material comprises a vegetable oil, a cross-linker comprised of a multi-functional  
alcohol, a catalyst, and a blowing agent, wherein said vegetable oil, said cross-linking  
agent, and said blowing agent are substantially non-esterfied prior to combining said A-side  
with said B-side.

20 65. A method of preparing a cellular material comprising the steps of combining an A-  
side material with a B-side material, wherein said A-side comprises a prepolymer  
diisocyanate and a B-side, wherein said B-side comprises a first vegetable oil, a cross-  
linking agent comprised of a multi-functional alcohol, a catalyst, and a blowing agent,  
wherein said vegetable oil, said cross-linking agent, and said blowing agent are  
25 substantially non-esterfied prior to combining said A-side with said B-side.

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US99/21511

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :C08G 18/00; C08H 5/00; C08J 9/34; C08L 75/00

US CL :521/51, 84.1, 109.1, 137, 151, 155

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 521/51, 84.1, 109.1, 137, 151, 155

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

NONE

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A,P	US 5,869,546 A (GRUSS et al) 09 February 1999, see entire document and column 2, lines 51 et seq, in particular.	1-61

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E* earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z* document member of the same patent family
*O* document referring to an oral disclosure, use, exhibition or other means	
*P* document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

28 OCTOBER 1999

Date of mailing of the international search report

16 DEC 1999

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

NATHAN M. NUTTER

Telephone No. (703) 308-0661

DEBORAH THOMAS  
PARALEGAL SPECIALIST